

Guangzhou Rodman Plastics Company Limited

Guangzhou Factory: 10 Shigang Road, Industrial Main Road South, Haizhu District, Guangzhou, PRC

Tel. (8620) 8435 4529 Fax. (8620) 8435 3638

Hong Kong office: 802 Car Po Commercial Bldg, 18-20 Lyndhurst Terrace, Central, Hong Kong

Tel. (852) 2854 1491 Fax. (852) 2815 3255

MATERIAL SAFETY DATA SHEET

General

Product Name: Ice bricks

(model ES3150 – Esky Ice pack lunch / model ES3300- Esky Ice pack All purpose /
model ES3600 – Esky Ice pack Six can / model ES3750 – Esky Ice pack Large)

Dangerous Goods Class: None Allocated

Subsidiary Risk: None Allocated

Poisons Schedule: None

Hazard Rating

0 – MINIMAL

1 – SLIGHT

2 – MODERATE

3 – SERIOUS

4 – SEVERE

5 – CHRONIC

Bottle – 0

Liquid – 0

Physical Description / Properties

Appearance: Blue Bottles and no smell & no colour liquid

Formula: Bottle [C₂H₄]_n, Liquid: Tap Water (H₂O), Salt (NaCl)

Boiling Point of liquid: 105 °C

Melting Point of bottle: 125 – 130 °C

Vapour Pressure: N/A

Specific Gravity: 0.03 (Water = 1)

Normal density of bottle: 0.914 and 0.925 g/cm

First Aid

Wash by water

Stability and reactivity

Stability: Stable

Condition to avoid: Temperature above 130 °C

Material to avoid: N/A

Hazardous polymerization: Will not occur

General Use

Put into refrigerator for freezing and then put in cooler.

Storage and transport

The product should be stored in a cool area for long life use. Keep away from heat and fire.



27/8/09



(TEST REPORT) 测试报告

No: SHFDO070703446FD-2

报告日期: 2007-07-26

客户名称: 广州洛民塑料有限公司上海分公司
 客户地址: 上海肇嘉浜路746号怡甸大厦5楼A1座

Client Name: (GUANGZHOU RODMAN PLASTICS CO. LTD.)
 Address:

样品由客户提供及申请者对样品的说明如下:

样品名称: 冰砖
 批号: 2008年8月
 生产商: 广州洛民塑料有限公司
 SGS流水号: SHFDO070703446FD-2
 样品接收日期: 2007-07-13
 样品测试日期: 2007-07-13 ~ 2007-07-20

PRODUCT: ICE BRICK
 PRODUCTION DATE: AUG 2006
 MANUFACTURER: GUANGZHOU RODMAN PLASTICS CO. LTD.
 SGS #:
 SAMPLE RECEIPT DATE: 13/7/2007
 TEST DATE: 13/7/2007 - 20/7/2007.

测试要求:
 根据申请者的要求:
 根据 GB 9687-1988 要求对样品进行检测

TEST REQUIREMENT: BASED ON GB 9687-1988 STANDARD OF PRC.

测试依据:
 GB 9687-1988 食品包装用聚乙烯成型品卫生标准

TEST BASIS: GB 9687-1988 STANDARD


测试结果: (TEST RESULT) (STANDARD) (RESULT) (PASS/FAIL)
 GB 9687-1988:

(TEST ITEM) 测试项目	(TEST METHOD) 测试方法	国家标准 GB 9687-1988	测试结果	单项判定
蒸发残渣, 4%乙酸, 60°C, 2h	GB/T 5009.60-2003	≤ 30 mg/L	8.5 mg/L	符合
蒸发残渣, 65%乙醇, 室温, 2h	GB/T 5009.60-2003	≤ 30 mg/L	5.5 mg/L	符合
蒸发残渣, 正己烷, 室温, 2h	GB/T 5009.60-2003	≤ 60 mg/L	9.8 mg/L	符合
高锰酸钾消耗量, 60°C, 2h	GB/T 5009.60-2003	≤ 10 mg/L	2.33 mg/L	符合
重金属(以铅计), 4%乙酸, 60°C, 2h	GB/T 5009.60-2003	≤ 1 mg/L	< 1 mg/L	符合
脱色试验(乙醇)	GB/T 5009.60-2003	阴性	阴性	符合
脱色试验(冷餐油)	GB/T 5009.60-2003	阴性	阴性	符合
脱色试验 (浸泡液)	水 60°C/2h	阴性	positive 阴性	positive 符合
	4%乙酸 60°C/2h	阴性	阴性	符合
	正己烷 20°C/2h	阴性	阴性	符合
	65%乙醇 20°C/2h	阴性	阴性	符合


Evaporation residue using 4%/65% ethanol & hexane
 potassium permanganate wastage
 Heavy metal (Pb)
 Decolor test (ethanol/buffet oil)

PASS

样品描述: 冰砖
 (PRODUCT: ICE BRICK)



页 1 / 1
 *** 结束 ***



This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or available on request and accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful and offenders shall be prosecuted to the fullest extent of the law.

SHFD 127340

7/F 3rd Building No 889, Yishan Road Shanghai, China 200233 | (86-21)61402666*2767 | (86-21)54500454 | www.cn.sgs.com
 中国·上海·宜山路889号3号楼7层 邮编: 200233 | (86-21)61402666*2767 | (86-21)54500454 | e.sgs.china@sgs.com

Member of the SGS Group (SGS SA)